# CALCINED KAOLIN

# Glomax™LL





Glomax LL is a dehydroxylated aluminum silicate produced by a controlled, hightemperature heating of a water-fractionated kaolin. Glomax LL is the standard of the coating industry as an extender pigment in paint systems where high whiteness and good opacifying properties are required. Glomax LL finds application in both solventand water-based coating systems as an extender for titanium dioxide and other prime pigments. Glomax LL, because of its medium-coarse particle size, provides good sheen control and excellent scrub resistance.

DAT005CK August 2001 ©IMERYS 2001 Second Edition

All product names are trademarks of IMERYS.

Glomax LL is used in polymers to provide stiffness, dimensional stability and good electrical properties. Because the product has been heat treated at a high temperature, Glomax LL also offers good heat and chemical resistance and a low moisture content.

#### IMFRYS

100 Mansell Court East Suite 300 Roswell, GA 30076

> General: Tel: (770) 594.0660 Fax: (770) 645.3384

> **Customer Service:** Tel: (888) 277.9636 Fax: (770) 645.3631

IMERYS is a business name of IMERYS Pigments, Inc., IMERYS Kaolin, Inc. and

IMERYS Marble, Inc. Registered in the USA.

This information is believed to be correct. However, this information does not constitute any representation, condition or warranty, nor do we guarantee results to be obtained. All recommendations and sales are made on the condition that we will not be held

resulting from their use. This provision may not be changed by any of our representatives.

liable for any damages

## **TYPICAL VALUES**

| Whiteness (L value)           | 96.5      |
|-------------------------------|-----------|
| Brightness (G.E. % of MgO)    | 91        |
| Particle Size, Median         | 1.5um     |
| Oil Absorption                | 53%       |
| pH, 20% Solids                | 4.5       |
| Free Moisture                 | 0.5% max. |
| Surface Area, B.E.T. Nitrogen | 9.0 m²/g  |
| Specific Gravity              | 2.62      |
| Refractive Index              | 1.62      |
| Residue (325 mesh screen)     | 0.02%     |

### **APPLICATIONS**

**Interior Emulsion Paints** Traffic Paint Electrical Wire and Cable Mechanical Rubber Compounds Ceramics Filled Polyamides Pharmaceutical Closures

